
DERBICOLOR XPS

Granule surfaced, triple reinforced APP modified bitumen waterproofing membrane

ADVANTAGES

- High quality 4.5 mm (180 mil) granule surfaced APP modified bitumen roofing membrane
- Performance Roof Systems' exclusive blend of APP (atactic polypropylene) polymers and select asphalts enhances the weathering capabilities and UV resistance of the membrane
- ➤ Triple reinforced with a heat resistant non-woven fiberglass mat followed by a fiberglass and polyester scrim that increases the membrane's strength and durability
- Mineral surfacing provides added resistance to weathering and foot traffic
- Meets and exceeds requirements of ASTM D6223, Type II, Grade G
- Can be applied with PERMASTIC Cold Adhesive or heat welded



TECHNICAL CHARACTERISTICS

DERBICOLOR® XPS Results*

PROPERTY	MD	XMD	ASTM
Peak Load @ 0°F; lbf/in	205	215	D5147
Peak Load @ 73.4°F; lbf/in	150	140	D5147
Elongation at Peak Load @ 0°F; %	5	5	D5147
Elongation at Peak Load @ 73.4°F; %	5	5	D5147
Tear Resistance @ 73.4°F; lbf	255	265	D5147
Dimensional Stability; %	< 0.5	< 0.5	D1204/D5147
Low Temperature Flexibility	Pass	Pass	D5147

PROPERTY	мимим	ASTM
Compound Stability @ 230°F	Pass	D5147
Granule Embedment; g	< 2	D4977/D5147

 $^{^{\}star}$ All values shown are nominal and subject to normal manufacturing tolerances.

PRODUCT INFORMATION*

PROPERTY	VALUE
Thickness; mil (mm)	180 (4.5)
Length; ft (m)	33.5 (10.2)
Width; in (m)	39.4 (1.0)
Weight; lb (kg)	110 (49.8)
Net Coverage; ft² (m²)	100 (9.2)

^{*} All values shown are nominal and subject to normal manufacturing tolerances

PACKAGING & STORAGE

Packaged 20 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather.

AVAILABLE COLORS









TOLL FREE: 800.727.9872 TEL: 816.921.0221