


DERBIGUM[®]P

Polyester reinforced APP modified bitumen waterproofing membrane

ADVANTAGES

- ▶ High quality 3.9 mm (152 mils) smooth surfaced APP modified bitumen roofing membrane
- ▶ Performance Roof Systems' exclusive blend of APP (atactic polypropylene) polymers and select asphalts enhances the weathering capabilities and UV resistance of the membrane
- ▶ Reinforced with a heat resistant a 180 gram polyester mat that increases the membrane's strength and durability
- ▶ Top placement of the reinforcement layers allow it to filter out harmful UV rays which reduces natural aging. Therefore the membrane does not require a granule surfacing or a roof coating for protection.
- ▶ Meets and exceeds requirements of ASTM D6222, Type I, Grade S
- ▶ Can be applied with PERMASTIC Cold Adhesive or heat welded



TECHNICAL CHARACTERISTICS

DERBIGUM[®] P Results*

PROPERTY	MD	XMD	ASTM
Peak Load @ 0°F; lbf/in	105	85	D5147
Peak Load @ 73.4°F; lbf/in	80	60	D5147
Elongation at Peak Load @ 0°F; %	10	10	D5147
Elongation at Peak Load @ 73.4°F; %	40	45	D5147
Ultimate Elongation @ 73.4°F; %	40	55	D5147
Tear Resistance @ 73.4°F; lbf	150	95	D5147
Dimensional Stability; %	< 0.5	< 0.5	D5147
Low Temperature Flexibility @ 32°F	Pass	Pass	D5147
Compound Stability; @ 230°F	Pass	Pass	D5147

* All values shown are nominal and subject to normal manufacturing tolerances.

PRODUCT INFORMATION*

PROPERTY	VALUE
Thickness; mil (mm)	152 (3.9)
Length; ft (m)	33.5 (10.2)
Width; in (m)	39.4 (1.0)
Weight; lb (kg)	96 (43.5)
Net Coverage; ft² (m²)	100 (9.2)

* All values shown are nominal and subject to normal manufacturing tolerances.

PACKAGING & STORAGE

Packaged 20 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather.



**PERFORMANCE
ROOF SYSTEMS**[™]
A SOPREMA GROUP COMPANY

www.performancerooftsystems.us
4800 Dr. Martin Luther King Jr. Blvd., Kansas City, MO 64130
TOLL FREE: 800.727.9872 TEL: 816.921.0221



Florida State
Wide Approval