

# PRS SA BASE

SBS modified bitumen self adhered base sheet

## ADVANTAGES

- ▶ High quality base sheet constructed from fiberglass mat coated with SBS modified bitumen
- ▶ Minimum SBS concentration is 8% and maximum filler concentration is 30% by weight of asphalt compound
- ▶ Fiberglass reinforcement increases strength and durability while also providing a smooth uniform base
- ▶ Meets or exceeds ASTM D4601 Type II specifications
- ▶ Self-adhering base applied without the use of torches, open flames, hot asphalt, or solvent-based adhesives

## TECHNICAL CHARACTERISTICS

### PRS SA Base Results \*

PROPERTY	MD	XMD	ASTM
Peak Load @ 73.4°F; lbf/in	<b>70</b>	<b>50</b>	D4601
Elongation at Peak Load @ 73.4°F; %	<b>135</b>	<b>135</b>	D4601

PROPERTY	MINIMUM	ASTM
Net dry mass; lb/sq	<b>35</b>	D4601
Asphalt mass; lb/sq	<b>15</b>	D4601
Surface and Stabilizer Filler; %	<b>35</b>	D4601

\* All values shown are nominal and subject to normal manufacturing tolerances.

## PRODUCT INFORMATION \*

PROPERTY	VALUE
Thickness; mil (mm)	<b>50</b> (1.27)
Length; ft (m)	<b>66.8</b> (20.4)
Width; in (m)	<b>36</b> (0.9)
Weight; lb (kg)	<b>62.4</b> (28.3)
Net Coverage; ft <sup>2</sup> (m <sup>2</sup> )	<b>180</b> (16.7)

\* All values shown are nominal and subject to normal manufacturing tolerances.

## PACKAGING & STORAGE

Packaged 25 rolls per pallet. Rolls should be stored on end, on raised platforms protected from the weather.

