## SENTINEL P150

Polyester Reinforced, 60 mil, Bare-Backed PVC Membrane

#### **DESCRIPTION**

SENTINEL P150 is a high-performance, bare-backed, thermoplastic polyvinyl chloride (PVC) membrane designed for both steep and low slope applications. SENTINEL P150 is reinforced with a tenacious, anti-wicking, weft-inserted polyester fabric that is encapsulated on both sides with a proprietary thermoplastic PVC formulation. SENTINEL P150 is available in a variety of colors, including white, gray and tan.


### **ADVANTAGES**

- ▶ Formulated utilizing only the highest quality polymers and plasticizers to produce consistent and reliable welds in a variety of ambient temperatures
- ► Manufactured with a minimum 30 mil thickness above scrim for a 60 mil sheet, adding durability and weathering resistance
- Reinforced with a high-density, polyester scrim that provides superior breaking strength as well as excellent puncture and fatigue resistance and durability
- Excellent resistance to inorganic chemicals and bacterial growth
- Meets or exceeds requirements of ASTM D4434, Type III

### **APPLICATION**

SENTINEL P150 is applied to approved substrates via mechanically attached, fully adhered or induction welded systems. For fully adhered systems, SENTINEL H2O or SENTINEL S Bonding adhesives are approved. Please refer to the specific product data sheet for application guidelines. For mechanically attached and induction welded systems, please consult your Performance Roof Systems' representative for specific fastening patterns. All laps must be heat-welded to ensure a water tight seal.

Refer to Performance Roof Systems' published technical literature for additional details and application requirements.




### **STORAGE & HANDLING**

Store rolls in a clean, dry location and cover as necessary to protect from environmental damage such as extreme cold, heat or moisture.

## **PRODUCT NUMBERS**

- P302 10 x 100 ft (3.0 x 30.5 m) Roll (White)
- P302-T  $10 \times 100$  ft (3.0 × 30.5 m) Roll (Tan)
- P302-G 10 x 100 ft (3.0 x 30.5 m) Roll (Gray)
- P302-H 5 x 100 ft (1.5 x 19.8 m) Roll (White)
- P302-H-T  $5 \times 100 \text{ ft} (1.5 \times 19.8 \text{ m})$  Roll (Tan)
- P302-H-G  $5 \times 100 \text{ ft} (1.5 \times 19.8 \text{ m})$  Roll (Gray)











# SENTINEL P150

Polyester Reinforced, 60 mil, Bare-Backed PVC Membrane

## **SHEET PROPERTIES**

PROPERTY	VALUE			
Technology	Thermoplastic polyvinyl chloride (PVC)			
ASTM standard	ASTM D4434, Type III			
Reinforcement	Polyester (18 x 9, weft inserted)			
Back surfacing	Bare-backed			

## DIMENSIONS & MASS

PROPERTY		VALUE	TEST METHOD		
<b>Length,</b> ft (m)	100 (30.5) 100 (30.5) 100 (30.5)		D4434		
Width, ft (m)	10 (3.0)	5 (1.5)	0.5 (0.15)	D4434	
Coverage,* ft² (m²)	650 (60.4) 325 (30.2) 50 (4.65)		D4434		
Roll weight, lb (kg)	329 (149.2)	165 (74.8)	17.1 (7.75)	D4434	
Rolls per pallet	10 10 20		D4434		
Pallet weight, lb (kg)	3,440 (1,560) 1,700 (771) 50 (4.65)		D4434		
Thickness, mils (mm)	60 (1.5)			D4434	
Thickness over scrim, mils (mm)	30 (0.76)			D4434	
Net mass per unit area, $lb/100 ft^2 (g/m^2)$	35 (1,722)			D4434	

<sup>\*</sup> All values shown are nominal and subject to normal manufacturing tolerances.

\*\*Coverage rate as reported assumes installation using side and end lap recommendations.

## **TECHNICAL CHARACTERISTICS\***

PROPERTY	MD	XMD	TEST METHOD	
Breaking strength; lbf/in	425 (74)	275 (48)	ASTM D751	
Elongation at break; %	30	30	ASTM D751	
Seam strength; min. 75% of breaking strength	Pass	Pass	ASTM D751	
Tearing strength; lbf	115 (512)	60 (267)	ASTM D751, Proc. B	
Trapezoidal tear; lbf	135 (601)	90 (400)	ATSM D751	
Low temperature bend @ -40°F	Pass	Pass	ASTM D2136	
Linear dimensional change @ 176°F; %	< 0.1	< 0.1	ASTM D1204	
Water absorption; %	<3	<3	ASTM D570	
Static puncture resistance @ ≥ 73°F; lbf (min. 15 kg)	Pass	Pass	ASTM D5602	
Dynamic puncture resistance; 20 J minimum	Pass	Pass	ASTM D5635	

 $<sup>^{\</sup>star}$  Data is represented by average values, unless noted otherwise.

## **ENERGY AND ENVIRONMENT**

PRODUCT	SOLAR REFLECTANCE ASTM C 1549		THERMAL EMITTANCE ASTM E 1371		<b>SRI</b> ASTM E 1980	
	INITIAL	3-YEAR	INITIAL	3-YEAR	INITIAL	3-YEAR
White	0.85	0.73	0.89	0.88	108	90
Gray	0.46	0.38	0.89	0.89	53	42
Tan	0.72	0.58	0.85	0.88	88	68





